

Military Powder Coat MLP20000

PPG Powder Coatings

Highlights

PPG's powder coatings for military applications provide a durable uniform finish for use in harsh military environments. PPG's Aliphatic Urethane Powder Coatings provide the combination of excellent UV durability, physical and chemical resistance properties that are required for the military coating market. Our unsurpassed application development program and technical service experts enable the consistently friendly use of these products on a variety of substrates.

PPG's powder coatings are available in low gloss FED-STD-595 military colors to meet the

requirements of the munitions and military equipment markets.

Product Features

This is a NON CARC product

Exterior durability

Good chemical resistance

Good corrosion resistance

Excellent exterior durability

Approved to ARDEC drawing specification #12998172

Technical Properties

Property	Test Method	Value
Color		33446 Desert Tan Federal Std 595
Appearance		Smooth
Gloss	ASTM D-523	2.0 - 7.0 @ 60°
Adhesion	ASTM D-3359	100% (5B Pass)
Hardness	ASTM D-3363	2H Pencil (Eagle)
Impact Resistance	ASTM D-2794	50 in-lbs Direct
Conical Mandrel	ASTM D-522	1/4" Mandrel - No cracking
Salt Spray	ASTM B-117	400 hrs
Xenon Arc	SAE J2527	700 hrs DE < 4.0

Film Properties were determined using 2.0 - 3.0 mils powder film over zinc phosphated, non-chrome rinse pretreated, 22 gauge, unpolished cold rolled steel test panels.

Application Data

Application Type: Electrostatic Spray

Recommended Bake: 20 Minutes at 395 °F Metal Temperature

See Cure Curve MLP-001

Specific Gravity: $1.62 \pm .05$

Theoretical Coverage: 119 Sq. Ft. per pound at 1.0 mil Shelf Life from Date of 80 °F Maximum - 24 Months

Manufacture (@ 40-60% RH):

should be tested prior to use.

PPG recommends that all material be used in FIFO order (first in - first out). Materials that exceed the recommended shelf life

PPG logo are registered trademarks of PPG Industries Ohio, Inc.

9/21/2022

^{*} Statements and methods described herein are based upon the best information and practices known to PPG Industries, Inc. ("PPG"). Any statements or methods mentioned herein are general suggestions only and are not to be construed as representations or warranties as to safety, performance, or results. Since the suitability and performance of the product is highly dependent on the product user's processes, operations, and numerous other user-determined conditions, the user is solely responsible for, and assumes all responsibility, risk and liability arising from, the determination of whether the product is suitable for the user's purposes, including without limitation substrate, application process, pasteurization and/or processing, and end use. No testing, suggestions or data offered by PPG to the user shall relieve the user of the responsibility. PPG does not warrant freedom from patent infringement in the use of any formula or process set forth herein. Continuous improvements in coatings technology may cause future technical data to vary from what is in this bulletin. Contact your PPG representative for the most up to date information.